



ATTACHMENT A

Claims 1 - 7: (Cancelled)

8. (Currently Amended) A polyolefin composition comprising:
- (A) from 60 to 85% by weight of a broad molecular weight distribution propylene polymer having a polydispersity index from 5 to 15 and a melt flow rate of from 20 to 78 g/10 min according to ASTM-D 1238, condition L; and
  - (B) from 15 to 40% by weight of a partially xylene-soluble olefin polymer rubber comprising at least 65% by weight of ethylene,

wherein the polyolefin composition comprises a melt flow rate of from 5 to 20 g/10 min.

9. (Previously presented) The polyolefin composition of claim 8 further comprising from 0.5 to 3 parts by weight of mineral fillers, with respect to the sum of components (A) and (B).

10. (Cancelled)

11. (Previously presented) The polyolefin composition of claim 8, wherein the partially xylene-soluble olefin polymer is a poly(ethylene-co-propylene).

12. (Cancelled)

13. (Previously presented) Articles produced comprising the polyolefin composition of claim 8.

14. (Cancelled)